

SECILTEK PK02

SYNTHETIC PLASTER

1. Description

SecilTek PK02 is a synthetic plaster made from acrylic resins in aqueous dispersion, ready to apply.

2. Usage

SecilTek PK 02 is a product intended to give the surfaces a smooth finishing.

It is applied on plaster, inside or outside, followed by painting. It doesn't crack and resists bacteria proliferation.



3. Product characteristics

Product in powder	
Aspect	White paste, slightly lustrous
Density	1.60+/- 0.05 kg/dm ³
pH	8.5 +/- 0.5
Viscosity	100+/- 5 KU
Theoretical Yield	1.6 kg/m ² /mm of thickness

4. Application:

Support preparation:

The supports must be clean, without any dust, disaggregated or instable matter, efflorescence, as well as any type of lowering to the normal conditions of adhesion.

Application

The application is made in conjunction with a heddle whenever it is needed during the coating in order to get the perfect finishing. The time needed to get dry in every coating may vary between 2 and 4 hours, in a normal condition of temperature (5°-30° degrees) and the relative humidity (must be less than 90%). Between the layers the surfaces shall be properly polished.

-

5. Package and Validity

SecilTek PK02 is delivered in plastic packages of 7 and 30kg.

The product, if its conditions to its original normal packaging conditions are not changed, has a validity of 6 months in storage conditions under the cover of extreme temperature and humidity.

6. Hygiene and safety

Please refer to Proyalbi for further information.

7. Warranty and Technical Assistance

For technical assistance and commercial information please contact

NORBERTO SANTOS / EDGAR FERREIRA

PHONE: 02 9787 8878

FAX 02 9703 0617

MOBILE: 0416 204 632 (NOBERTO)

0412 075 166 (EDGAR)

PO Box 272

PETERSHAM NSW 2049

email: norberto@proyalbi.com.au

web: www.proyalbi.com.au

The information and technical data contained herein reflect our present knowledge and may be altered without notice. Our responsibility is limited to the quality warranty of product supplied and any anomalies resulting from its undue application are rejected.

Should this document arise any doubts, mainly in reference to particular building aspects, please contact our Technical Services.